

# FISCHER PLASTIK

Gesellschaft m.b.H.

A-4511 Allhaming 101, Tel.:07227 7181, Fax: 07227 718122

Polyäthylen, die  
umweltfreundliche  
Verpackung –  
recyclbar

Herstellung von Folien, Schläuchen, Säcken, Tragtaschen aus HD-, LD-Polyäthylen  
unbedruckt und bedruckt, Automatenrollen, Putzereischläuche, Schrumpffolien,

FirmenbuchNr.: FN 119762  
UID-Nr.: ATU 22518309

## Technical Data Sheet HDPE

**Product:** zfh0-00-045-032-02-00-00 HDPE-SHEET 450x320mm/20µm

| Properties (standard values) |                   |                      |
|------------------------------|-------------------|----------------------|
| Material                     |                   | HDPE<br>Polyethylene |
| Melt Index MFR 190/21,6      | g/10 min          | 7,0-9,0              |
| Density (23 °C)              | g/cm <sup>3</sup> | 0,94-0,955           |
| Vicat Softening Temperature  | °C                | 128                  |
| Additives                    |                   | yes                  |
| Colour                       |                   | no                   |

### Traceability:

FISCHER-PLASTIK has implemented appropriate systems and procedures that ensure traceability at all stages of production. Units of quantities are marked – usually with order confirmation numbers – in order to trace back the supply chain.

### Usage

At room temperature resistant to inorganic acids (highly oxidizing excluded), bases, salts and their solutions, marginal swelling in case of contact with alcohol, fat, oil (of animal or vegetable origin) and wax possible.

The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

**Storage:** Store the product in dry storehouses at temperatures below 50°C. Polyethylene should not be exposed to UV radiation. FISCHER-PLASTIK does not take responsibility for any damages caused by adverse storage. Storable at least for eight months.

### FISCHER-PLASTIK Ges.m.b.H.

Place and Date of issue  
Allhaming 20-10-2014

*This document is created electronically and is valid without signature*  
Validity: 12 months